

#### 9347 - 193 Street, Surrey, B.C. V4N 4E7 Canada Phone: (604) 888-3084 Toll Free: 1-800-201-8822 Fax: (604) 888-7754


Toll Free: 1-800-708-9888

ISO 9001 Registered Quality System Burlington, Ontario, Canada QMI Certificate # 004008

### **Super Thermal Grease**

Designed for use with heat sinks to effectively dissipate heat generated by electronic devices and circuitry. Ideally used to cool CPUs (when over clocking), chipset and graphics cards.

Formulated with Boron Nitride, this grease gives super high thermal conductivity without the capacitance issue associated with silver filled greases.



## **Key Features:**

- Thermal conductivity of 3.0 w/(m·k)
- Contains no silicone or metal particles
- Pigmented with Boron Nitride particles
- Maximum operating temperature of 150 °C / 302 °F

### It is important to properly cool your system for maximum reliability and to prevent premature failure.

Heat sinks alone are not entirely effective at keeping your system efficiently cooled do to the imperfections on the surface of your circuitry and the heat sink. See flash demonstration on our website, http://www.mgchemicals.com/techsupport/860\_demo.html

The use of our Super Thermal Grease will assist the heat sink to provide you with superior heat dissipating ability.

# Specifications

**Typical properties:** 

**Test Method** 

Phase:	Highly viscous	
Base:	Blend of Synthetic Fluids	
Odor:	Odorless	
Color:	White	
Specific Gravity:	1.2 g/L	
Flash point:	165 °C	
Autoignition temp.:	$> 315 \ ^{0}C$	
Solubility in water:	Insoluble	
VOC:	Zero	
Vapor Density:	> 5 (Air =1)	
RoHS complaint:	Yes	
Corrosiveness	Non-Corrosive	



9347 - 193 Street, Surrey, B.C. V4N 4E7 Canada Phone: (604) 888-3084 Toll Free: 1-800-201-8822 Fax: (604) 888-7754

Toll Free: 1-800-708-9888

ISO 9001 Registered Quality System Burlington, Ontario, Canada QMI Certificate # 004008

Thermal Properties		
Thermal conductivity	ASTM D5470	in W/mK
Temperature in <sup>0</sup> C		
50		2.97
100		2.98
150		3.00
Thermal limits		
Peak		-40C to +175C
Long term		-15C to + 150C

<b>Electrical Properties</b>		
Dielectric Strength	ASTM D150	170 Volts/mil
(Tested at 1 MHz @ ambient		
condition)		
Dielectric Constant	ASTM D150	4.2
(Tested at 1 MHz)		
Dissipation Factor	ASTM D150	0.001
(Tested at 1 MHz)		
Volume Resistivity	ASTM D257	1.2 X 10 <sup>12</sup> Ohms.cm
(Tested at ambient condition)		

# **Available Sizes**

Catalog Number	Sizes Available	Description
8615	3.5 gram (0.12 oz)	Syringe